

Product Data Sheet

HYTHERM ECO XPS

Insulation for Inverted Roofs

Hytherm ECO XPS is a rigid extruded polystyrene XPS insulation board for use in Axter inverted warm roof applications in conjunction with Axter's Water Flow Reducing Layer (WFRL).

Hytherm ECO XPS insulation uses carbon dioxide as a blowing agent, which gives it an ozone depleting potential (ODP) of zero and a Global Warming Potential (GWP) of less than 5.

It is available in a range of thicknesses to meet the performance requirements of specific applications.

A manufacturers BBA certificate is available.



Key benefits

- This multi-purpose board provides thermal insulation and frost protection for inverted, warm roofs with a variety of roof coverings including accessible, living and blue roofs.
- Infrared particles are finely dispersed and incorporated into the extruded cell walls. These scatter and reflect heat radiation, helping to reduce heat transfer to keep a building warm in winter and cool in summer.
- Declared thermal conductivity of 0.030 W/m.K for thicknesses up to and including 120mm and 0.031 W/m.K for thicknesses above this.
- Global Warming Potential (GWP) of less than 5.
- Ozone depleting potential (ODP) of zero.
- Closed cell structure for load-bearing applications, rated for;
 - 300 kPa compressive stress (according to BS EN 826:2013).
 - 130 kPa compressive creep (2% deformation after 50 years according to BS EN 1606:2013).
- Has low water absorption (<0.7% according to EN 12087), is temperature stable from -50 to 75°C, and <5% dimensional stability (according to BS EN 1604:2013).
- Can be cut using hand tools.
- A manufacturer's BBA certificate is available.
- Achieves CE marking.

Use

Hytherm ECO XPS is designed for use as insulation on inverted roofs. The insulation satisfies thermal performance and strength requirements of demanding project specifications for the lifetime of the structure. It can be used on untrafficked flat roofs as well as balconies (subject to consideration for external fire spread regulations) and terraced roofs with pedestrian access only.

In comparison to most other typical roof insulation types, the boards are robust and highly resistant to the conditions often present on a flat roof, including wide temperature fluctuations and repeated freeze/thaw cycles.

Hytherm ECO XPS is intended for use on heavyweight decks such as reinforced concrete with a ballast layer of gravel or concrete slab. It can also be used on metal or timber decks. Concrete, metal or timber roofs should be designed in accordance with the relevant provisions BS 6229, BS 8217 and BS 8218, particularly to accommodate the weight of the ballast layer.

Hytherm ECO XPS must be overlaid with Axter filter/water flow reducing layer (WFRL) which acts as a filter layer preventing fines and other debris from passing through and also reducing the amount of rainwater flow into the insulation layer voids adversely affecting the overall thermal performance of the insulation layer. This membrane must be laid with 300mm laps and covered with a gravel ballast or paving finish. Hytherm ECO XPS should be laid in a brick-bond pattern. It is essential that all joints between boards are tight and that no gaps exist when meeting rooflights, edge details and other services which perforate the roof deck.

These insulation boards are compatible with most construction materials, e.g. lime, cement, plaster, solvent-free bituminous compounds, water-based preservatives, anhydrous gypsum, alcohols, acids and alkalis. The use of solvent-free adhesives is advised; please contact Axter Ltd for more information on compatibility. Certain organic materials such as solvent-based wood preservatives, coal tar and derivatives (creosote), paint thinners and common solvents (acetone, ethyl acetate, petrol, toluene and white spirit for example) will attack Hytherm ECO XPS which could lead to loss of performance through softening, shrinkage and possible dissolution.

Durability

When properly installed with the water flow reducing layer in place, Hytherm ECO XPS boards will remain an effective insulant for at least 25 years.

Environmental

Hytherm ECO XPS is non biodegradable and does not present an environmental hazard.

The material can be recycled, disposed of as landfill or incinerated to recover the energy content.

Fire

Hytherm ECO XPS contains a flame retardant additive to inhibit accidental ignition from a small fire source. However, it is combustible and if exposed to an intensive fire may burn rapidly. Therefore, during shipment, storage, installation and use, Hytherm ECO XPS should not be stored close to open flames or other ignition sources or come into contact with volatile organic compounds and chemicals such as solvents. During installation, Hytherm ECO XPS products should be protected from direct exposure to fire.

Hytherm ECO XPS achieves Euroclass E (reaction to fire) to standard BS EN 13501-1:2018 Fire classification of construction products and building elements.

In accordance with European Commission Decision 2000/553/EC, when covered with either 4mm-32mm aggregate(*) (minimum 50mm depth) or cast stone or mineral slabs (minimum 40mm thickness), the roof may be considered to be unrestricted by the national Building Regulations. Other roof coverings should be confirmed as required.

(*) Note that whilst the European Commission Decision quotes 4mm-32mm aggregate, it is commonplace in the UK that the aggregate is 20mm-40mm diameter. However, this should be assessed and confirmed by the project lead designer.

Handling and Storage

Hytherm ECO XPS is lightweight and easy to handle and install. The product must be protected from prolonged exposure to sunlight to prevent degradation of the surface of the board.

Product Characteristics

Thermal resistance*															
Thickness (mm)	50	80	100	115	120	130	140	145	160	165	175	180	190	195	200
R _d m ² .K/W(mm)	1.65	2.65	3.30	3.80	4.00	4.15	4.50	4.65	5.15	5.30	5.60	5.80	6.10	6.25	6.45

*Thickness dependant.

Hytherm ECO XPS is supplied as a lap jointed board.

Properties	Unit	Value	Standard	EN code
Dimensions and tolerances				
Length	mm	1250	BS EN 822:2013	-
Width	mm	600	BS EN 822:2013	-
Thickness tolerances	Class	1	BS EN 823:2013	T
Mechanical Properties				
Compressive strength or compressive stress at 10% deformation	kPa	300	BS EN 826:2013	CS(10\Y)

Properties	Unit	Value	Standard	EN code
Compressive creep max after 50 yrs <2% deformation under stress	kPa	130	BS EN 1606:2013	CC(2/1.5/50) σ
Hygrometric properties				
Long term water absorption by total immersion	Vol-%	<0.7	BS EN 12087:2013	WL(T)
Water pick up by diffusion	%	2 <80mm 1 \geq 80mm	BS EN 12088:2013	WD(V)
Water pick up after Freeze Thaw	%	<1	BS EN 12091:2013	FTCD
Thermal Conductivity				
Thermal Conductivity Declared	W/m.K	0.030 \leq 120mm 0.031 >120mm	BS EN 13164:2012+A1:2015	λ_D
Other properties				
Reaction to fire classification	-	E	BS EN 13501-1: 2018	Euroclass
Linear thermal expansion coefficient (typical)	mm/(m.K)	0.07	-	-
Temperature limits	°C	-50/+75	-	-
Dimensional stability under specified temperature (70°C) and humidity conditions (90%rh)	%	< 5	BS EN 1604:2013	DS(70,90)
Colour	-	Grey	-	-
Surface finish	-	Skin	-	-
Edge profile	-	Ship lap	-	-
EN designation code: XPS-EN 13164-T1-CS(10\Y)300-CC(2/1.5/50)130-DS(70,90)-DLT(2)5-WL(T)0.7- WD(V)1,2,3(1)-FTCD1				

1 N/mm² = 1000 kPa = 1 MPa

Axter Ltd reserves the right to modify and update this data at any time without prior notice. Only the latest version of this document is valid, available for download at www.axter.co.uk/downloads. Once downloaded, documents are uncontrolled. Users should always confirm they are referring to the latest version prior to use. Further assistance is available from Axter Ltd's Technical Support Team, email: technical@axterltd.co.uk, telephone: 01473 935008.

The intended use of this product should be verified with Axter Ltd prior to adoption to ensure its suitability and compliance with specifications, project requirements, industry regulations, legislation, good practice, installation techniques and all other relevant guidance. Axter Ltd accepts no liability for non-compliant use of this product.