

# Technical Data Sheet

## WILOTEKT SURFACE CONDITIONING PRIMER Wilotekt®-Plus Structural Waterproofing System

<b>1. Description</b>	Wilotekt Surface Conditioning Primer is a black, liquid, toluene free, fast drying*, cold bitumen primer. It is supplied ready to use as part of the Wilotekt-Plus structural waterproofing system.
<b>2. Use</b>	Primer used to aid the bonding of bituminous waterproofing membranes on to concrete, metal and timber support structures.
<b>3. Packaging</b>	Wilotekt Surface Conditioning Primer is supplied in 25L drums.
<b>4. Storage</b>	Containers should be kept upright. The drums must be stored in cool, ventilated, dry conditions and away from naked flames and electrostatic charge. Shelf life (sealed in unopened, original packing): 12 months from date of manufacture.
<b>5. Instructions for use</b>	Coverage (Indicative): 150 - 300g/m <sup>2</sup> . Drying time: 30 to 60 minutes*. Ensure support structures are dry and clean with no loose particles. Metal surfaces should be rust- and grease-free. Application: Brush or roller apply the Wilotekt Surface Conditioning Primer to the prepared, clean and dry structure and allow to dry completely before continuing the application of the remaining Wilotekt-Plus waterproofing components. Installation details of the Wilotekt-Plus system are shown in the Axter Wilotekt-Plus Brochure available from: <a href="http://www.axter.co.uk/downloads">www.axter.co.uk/downloads</a> . The Wilotekt-Plus system must be installed by Axter accredited installers who have completed upskilling in this system. More information is available here: <a href="http://axter.co.uk/installer-membership">axter.co.uk/installer-membership</a>

<b>6. Safety and handling</b>	<p>Anyone handling this product should be aware of suitable working techniques, gestures and postures.</p> <p>Operatives should use appropriate personal protective equipment.</p> <p>For full details refer to the Wilotekt Surface Conditioning Primer Safety Data Sheet (SDS).</p>
<b>7. Disposal / Re-use</b>	<p><b>Disposal</b> Proper waste management of the mixture and/or its container must be carried out in accordance with current regulations. Refer to the Wilotekt Surface Conditioning Primer SDS.</p> <p><b>Re-use</b> When installed as part of a complete hot melt waterproofing system, the product becomes an integral part of the structure that cannot be removed for processing and is disposed of at the end of life of the structure.</p>
<b>8. Additional documents</b>	Axter Wilotekt-Plus Brochure
<b>9. Certification</b>	<p>The Wilotekt-Plus Hot Melt Waterproofing System holds the below certification:</p> <p>BBA 22/6518          ETA 03-0049          EPD 3554</p> <p>Manufactured within ISO 19001 and ISO 14001 certified management systems.</p> <p>All certification documents are available at <a href="http://www.axter.co.uk/downloads">www.axter.co.uk/downloads</a></p>

CHARACTERISTICS	
Presentation	Liquid
Colour	Black
Density	0.92g/cm <sup>3</sup>
Viscosity (in accordance with ASTM D445)	46mm <sup>2</sup> /s (40°)
Flash Point	26°C
Drying time	30 - 60 minutes*

\* This can vary depending on climatic conditions.

Axter Ltd reserves the right to modify and update this data at any time without prior notice. Only the latest version of this document is valid, available for download at [www.axter.co.uk/downloads](http://www.axter.co.uk/downloads). Once downloaded, documents are uncontrolled. Users should always confirm they are referring to the latest version prior to use. Further assistance is available from Axter Ltd's Technical Support Team, email: [technical@axterltd.co.uk](mailto:technical@axterltd.co.uk), telephone: 01473 935008.

The intended use of this product should be verified with Axter Ltd prior to adoption to ensure its suitability and compliance with specifications, project requirements, industry regulations, legislation, good practice, installation techniques and all other relevant guidance. Axter Ltd accepts no liability for non-compliant use of this product.